

## Jelinek Cork Floating Floor Specifications

SPECIFICATIONS		
PROPERTY	REQUIREMENT	TEST METHOD
WIDTH	+/- 0.50mm	NP EN 427
LENGTH	Max. 2.0mm	
THICKNESS	+/- 0.25mm	NP EN 428
SQUARENESS	≤ 0.5mm	NP EN 427
STRAIGHTNESS	≤ 0.3mm	EN 427
FLATNESS OF THE PANEL		NP EN 14085
LENGTH CONCAVE/CONVEX	≤ 0.50 / ≤1.0	
WIDTH CONCAVE/CONVEX	≤ 0.10 / ≤ 0.15	
OPENINGS BETWEEN PANELS	≤ 0.15 mm	NP EN 14085
HEIGHT DIFFERENCE BETWEEN PANELS	≤ 0.15 mm	NP EN 14085
BEHAVIOUR OF THE BONDING	There shall be no delamination at all.	NI
HIGH DENSITY OF FIBREBORD (HDF)	≥ 800 kg/m <sup>3</sup>	NP EN 672
WEAR RESISTANCE	3.6 mg / 100 ciclos (Loss Weight)	DIN EN 660-2
TENSILE STRENGTH	≥ 170 N/50mm	NI
Specifications according with EN 14085, Resilient floor coverings - Specification for floor panels for loose laying.		